





















TECHNICAL CHARACTERISTICS

wineo 600						wineo
Heterogeneous resilient-flooring for glueless installation - Covering type according to EN ISO 10582						
	wineo 600 wood	wineo 600 wood „Patchwork“	wineo 600 wood XL	wineo 600 stone	wineo 600 stone XL	
Format	1212 x 187 mm	1212 x 185 mm	1505 x 237 mm	600 x 317 mm	914 x 480 mm	
Product thickness	5 mm	5 mm	5 mm	5 mm	5 mm	
Planks, tiles / m² per box	8 / 1.81 m ²	8 / 1.79 m ²	6 / 2.14 m ²	10 / 1.90 m ²	6 / 2.63 m ²	
Boxes / m² per pallet	64 / 115.84 m ²	64 / 114.56 m ²	56 / 119.84 m ²	60 / 114.00 m ²	44 / 115.72 m ²	
Guarantee	20 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de					
Classification						Product composition
	Utilization class 23 EN ISO 10874		Heavy-duty use in the domestic area			1 Surface sealing
	Utilization class 32 EN ISO 10874		Normal use in the commercial sector			2 Surface texture various embossings
	Utilization class 41 EN ISO 10874		Medium use in the light industrial sector			3 Wear layer Thickness 0.4 mm
	Wear layer binder content EN ISO 10582		Type I			4 Decor Decor film
	Anti slip category DIN 51130		R 9			5 Base layer with glass fibre reinforced
	Staining and chemical resistance EN ISO 26987		Good resistance according to the concentration and residence time			6 Profile connection Connect technology 
	Light fastness EN ISO 105-B02		Light fastness (method 2) ≥ 6			7 Backing
	Residual indentation EN ISO 24343-1		≤ 0.1 mm			Insulation mat silentCOMFORT (seperately available)
	Castor chair test ISO 4918		25000 revolutions no damage with rolls type W			
	Thermal resistance EN 12667		≤ 0.021 (m ² K)/W without insulation mat ≤ 0.031 (m ² K)/W with insulation mat silentCOMFORT			
	Impact sound reduction EN ISO 16251-1		~ 7 dB up to 14 dB in combination with silentCOMFORT			
	Dimension stability EN ISO 23999		~ 0.1 %			
	Disposal		Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203			
 <p>Windmüller GmbH Nord-West-Ring 21 D-32832 Augustdorf</p> <p>DOP: 0301010 EN 14041:2004 / AC2006 1658</p>    <p>www.wineo.de</p>						
<p>ÉMISSIONS DANS L'AIR INTÉRIEUR*</p>  <p>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (tres faibles émissions)</p>						
<p>Phthalat frei 100% Phthalate free</p> <p>factory made coated</p>						

Relevant information:

- Installation in utilization class 41 possible (vehicular traffic excluded).
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.